



Technical Data Sheet

Page 1 of 2

Properties:

AKEMI® Spider Black is a fast hardening product made of highly efficient waxes and synthetic resins, dissolved in hydrocarbons. It hides and darkens spider veins and micro fissures, give a brilliant polish along with a strong colour intensification. The surface becomes water-repellent.

Application Area:

AKEMI® Spider Black can be applied on fine ground or polished natural and artificial stone, e.g. marble, granite, slate, terrazzo, travertine for indoor use. Due to the black colour excellent results are achieved on dark and black stones.

Instructions for Use:

- 1. Clean the surface thoroughly with AKEMI® Stone Cleaner. It must be clean and absolutely dry before use. Ideal temperature for application 15 25°C.
- Apply a thin layer with a cloth or brush, for larger areas apply with a mop.
- 3. Repeat application on very absorbent, non-polished surfaces.
- 4. Ideal moment for polishing has come when surfaces show a matt appearance. Re-polish surfaces with a soft cloth or a white nylon pad and a floor polishing machine.
- 5. For regular cleaning use AKEMI® Mild Stone Soap or AKEMI® Crystal Clean.

Special Notes:

- For professional use only.
- Objects in the working area which are not resistant to solvents, s.a. various synthetic materials, rubber, lacquered areas, must be protected.
- At temperatures below 9°C the product becomes viscous, below 0°C it becomes almost solid.
- Storage at a temperature of 15°C will render it ready to be worked again.
- Apply the product in a thin layer, only, otherwise the surface will not take a good polish.
- Films of AKEMI[®] Spider Black can be removed by AKEMI[®] Wax Stripper.
- For proper waste disposal, the container must be completely emptied.
- Recycling in accordance with the guidelines of EU Decision 97/129 EC on the Packaging Directive 94/62/EC.

Technical Data: Coverage: approx. 15 - 30 m²/liter; depending on the surface

finish

Colour: black

Density: approx. 0.78 g/cm³

Storage: If stored in dry and cool condition (5-25°C/41-77°F) in its closed original

container at least 24 months from production.

Health & Safety: Read Safety Data Sheet before handling or using this product.





Technical Data Sheet

Page 2 of 2

Important Notice:

The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trails of the product, in an inconspicuous area or fabrication of a sample piece.